

Amendments to the Specification

Please amend page 15, ll.14-23 as follows.

When the amount of the petroleum resin is less than 5% by weight, the film may not have sufficiently low shrinking properties. When the amount of the petroleum resin exceeds 40% by weight, the laminate film often has a specific gravity of 0.950 or more. When the laminate film having such a specific gravity is used as a covering film of a bottle made of a saturated polyester resin, it may ~~sometimves~~ sometimes be difficult to accurately separate the film from the polyester resin by a liquid-specific gravity method in recycling the polyester resin.